

ELASTOSIL[®] M 4119 A/B

ELASTOSIL[®]

Room Temperature Curing Silicone Rubber (RTV-2)

Pourable, addition-curing RTV-2 silicone rubber that cures at room temperature.

Main application: Making shrink-free molds with excellent reproduction accuracy.



Properties

- Low viscosity
- Low hardness (Shore A 20)
- Easy to meter and mix due to 1:1 ratio
- Short curing time at room temperature
- Translucent
- Non shrink cure
- Easy demolding

Technical data

Properties Uncured

Property	Condition	A	B	Method
Viscosity, dynamic	-	3000 mPa·s	4000 mPa·s	Brookfield
Density	-	1.05 g/cm ³	1.05 g/cm ³	-
Color	-	-	tranlucend	-

These figures are only intended as a guide and should not be used in preparing specifications.

Catalyzed

Property	Condition	Value	Method
Pot Life up to 100000 mPas	-	7 min	-
Mix ratio	-	1:1 pbw	-
Color	-	translucent	-
Demoldable	-	35 min	-

These figures are only intended as a guide and should not be used in preparing specifications.

Properties Cured

After 24 hours at 23°C

Property	Condition	Value	Method
Elongation at break	-	> 400 %	ISO 37
Tensile strength	-	3.5 N/mm ²	ISO 37
Hardness Shore A	-	20	-

These figures are only intended as a guide and should not be used in preparing specifications.

All the information provided is in accordance with the present state of our knowledge. Nonetheless, we disclaim any warranty or liability whatsoever and reserve the right, at any time, to effect technical alterations. The information provided, as well as the product's fitness for an intended application, should be checked by the buyer in preliminary trials. Contractual terms and conditions always take precedence. This disclaimer of warranty and liability also applies particularly in foreign countries with respect to third parties' rights.

Applications

- Reproduction molding for foundry, arts and handicraft

Application details

As a low-Shore addition-curing RTV-2 silicone rubber that cures without undergoing dimensional shrinkage, ELASTOSIL® M 4119 is extremely suitable for casting all common reproduction materials, particularly if accurate copies of models with pronounced undercuts are required. Perfect mold making material for very fast de-moldings!

Processing

ELASTOSIL M 4119 proc

Mix components A and B in a ratio of 1 : 1.

Important note:

The platinum catalyst is contained in **component A**.

Caution:

A and B components may only be used together if they have the same batch number.

Please check also our brochures and info sheets

Packaging and storage

Storage

Storage

The "Best use before end" date of each batch is shown on the product label.

Storage beyond the date specified on the label does not necessarily mean that the product is no longer usable. In this case however, the properties required for the intended use must be checked for quality assurance reasons.

Safety notes

Components A and B of the addition-curing grade ELASTOSIL® M 4119 A/B contain only constituents that over many years have proved to be neither toxic nor aggressive. Special handling precautions are therefore not required, i.e. only the general industrial hygiene regulations apply.

Detailed safety information is contained in each Material Safety Data Sheet, which can be obtained from our sales offices.

QR Code ELASTOSIL® M 4119 A/B



For technical, quality or product safety questions, please contact:

Wacker Chemie AG, Hanns-Seidel-Platz 4, 81737 Munich, Germany
info@wacker.com, www.wacker.com

The data presented in this medium are in accordance with the present state of our knowledge but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this medium should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. The information provided by us does not absolve the user from the obligation of investigating the possibility of infringement of third parties' rights and, if necessary, clarifying the position. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the product for a particular purpose.